

L28 ANSWER 72 OF 75 HCAPLUS COPYRIGHT 2007 ACS on STN

ACCESSION NUMBER: 1990:180148 HCAPLUS Full-text

DOCUMENT NUMBER: 112:180148

TITLE: Manufacture of fire-resistant polyesters

INVENTOR(S): Matsumoto, Tetsuo; Imamura, Takayuki; Azeyanagi, Akiko; Tsujimoto, Keizo; Hamada, Shunichiro

PATENT ASSIGNEE(S): Japan Ester Co., Ltd., Japan

SOURCE: Jpn. Kokai Tokkyo Koho, 6 pp.

CODEN: JKXXAF

DOCUMENT TYPE: Patent

LANGUAGE: Japanese

FAMILY ACC. NUM. COUNT: 1

PATENT INFORMATION:

PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
-----	----	-----	-----	-----
JP 01284521	A	19891115	JP 1988-114150	19880511 <--
JP 07033437	B	19950412		

PRIORITY APPLN. INFO.:

JP 1988-114150

19880511 <--

ED Entered STN: 12 May 1990

AB The title polyesters are manufactured without lowering mech. strength by copolyng. 1-10 mol% (based on total acid components) ester-forming functional group-containing unsatd. compds. to polyesters at $\leq 260^\circ$ to intrinsic viscosity 0.25-0.48, then polycondensing with 0.7-1.0:1 (equivalent ratio, based on unsatd. bonds of the copolynd. unsatd. compds.) PHR₁R₂(O)_n (R₁, R₂ = C₁-20 alkyl, C₆-20 aryl, C₁-20 alkoxy, C₆-20 aryloxy; R₁R₂ may be bonded to form a ring; n = 0, 1) at $\leq 270^\circ$ to intrinsic viscosity ≥ 0.5 . Thus, a slurry of (1.6:1, mol ratio) ethylene glycol (I) and terephthalic acid was added to bis(β -hydroxyethyl) terephthalate and its oligomers and heated at 255° , then treated with (1:0.8, mol. ratio) maleic anhydride (II)-I mixture (II content is 2.5 mol% of total acid components) at 260° in the presence of GeO₂ to give a polyester with intrinsic viscosity 0.45, which was treated with 2.0 mol% (based on total acid components) 9,10-dihydro-9-oxa-10-phosphophenanthrene-10-oxide at 260° and 0.3 torr to give a fire-resistant polyester with intrinsic viscosity 0.65 and m.p. 250° showing good strength.